

TEST REPORT

Issued To : **DIAMOND INTERNATIONAL INEX PRIVATE LIMITED**
PLOT NO.98, SECTOR-8,
IMT MANESAR,

GURGAON-122001

Report No.: 141007017/1410070051 Date: 15-Nov-2014
Sample Description : DOR 07-Oct-2014
DIAMOND GLASS FIBER REINFORCED (GRG) CEILING TILE TYPE 8811, 12M
M THK

Phone/Fax:
Kind Attn. :

Your Ref. No. :

ID:1410070051

HUMIDITY RESISTANCE TEST

TEST	REQUIREMENT	RESULT
<p>Test Condition: a) Temperature: 27°C b) Relative Humidity: 99% c) Test duration: 336 hrs</p> <p>Observation: <u>Humidified Deflection:</u> mm</p>	8(Max)	6

Protocol: ASTM C 473-03/ASTM C 1396-04



[Signature]
Analyst



ASHOK GIRI
SR. ANALYST
[Signature]
Authorised Signatory