

TEST REPORT

Issued To : DIAMOND INTERNATIONAL INEX PRIVATE LIMITED
PLOT NO.98, SECTOR-8,
IMT MANESAR,
GURGAON-122001

Report No.: 141007017/1410070050 Date: 15-Nov-2014
DOR 07-Oct-2014

Sample Description :
DIAMOND MINERAL FIBER CEILING TILE TYPE APT-002, 16MM THK

Phone/Fax:
Kind Attn. :

Your Ref. No. :

ID:1410070050

HUMIDITY RESISTANCE TEST

TEST	REQUIREMENT	RESULT
<p>Test Condition: a)Temperature:27⁰C b)Relative Humidity:99% c)Test duration:336 hrs</p> <p>Observation: <u>Humidified Deflection:</u> mm</p>	8(Max)	8

Protocol:ASTM C 473-03/ASTM C 1396-04

Page 3 of 3



[Signature]
Analyst



[Signature]
Authorised Signatory

TEST REPORT

Issued To : **DIAMOND INTERNATIONAL INEX PVT. LIMITED**
309, UDYOG VIHAR PHASE II

Report No.: 110329011/1103290025

Date: 11-Apr-2011
DOR 29-Mar-2011

Sample Description :
MINERAL FIBER TILES

GURGAON- 121001

Phone/Fax: 0124 4308025, 4308026,
Kind Attn: MR. B B PURI

Your Ref. No. :

ID-1103290025

S.N. Test /Conditioning

Results

1. **Humidity Resistance Test**

No Cracks & blisters observed

Temperature - 27°C
Humidity - 95%
Time - 48 hours

Protocol: Guideline of ASTM C-1396M & 473



[Signature]
Analyst: CCREQD\2\IRA000\IA5956

Authorised Signatory

TRA- 052477

NABL accredited, BIS, DGS & D, DDA, MOEF, DGCA approved,
ISO - 9001: 2008 & ISO 14001 : 2004 Certified Laboratory
Subject to Terms & Conditions Overleaf