



# TEST REPORT

Page 1 of 2

<b>Report Issued To</b>	<b>Diamond International Inex Pvt Ltd</b>	<b>Report No.</b>	<b>N5104</b>
	Plot 98, Sec 8, IMT Manesar, Gurgaon, Haryana 122050	<b>ULR-</b>	<b>TC733224000004215F</b>
		<b>Date Received</b>	<b>12-02-2024</b>
		<b>Date Issued</b>	<b>15-02-2024</b>

## Client Information

Recipient	Mr Raman Mehta
Recipient Email	raman@diamonddtm.net

## Sample Information

Sample Description:	DES.- METAL CEILING TILE, ITEM- RA 24, SIZE- 595x595 MM
Conformity Specification	--

**“Refer to page 2 for test result summary and appropriate notes.”**

- Note:** - 1. Sample Will be retained only for three months.  
2. Any complaints about report should be communicated within 7 days from the date of issued.  
3. This report cannot be used as an evidence in a court of law and should not be given to any external party partially without prior written permission of laboratory.  
4. Total liability of our laboratory is limited to the invoiced amount. No liability will be accepted after the sample received by customer.  
5. This test report may not be reproduced in whole or in part, without written approval of WIDMANS LABORATORY (P) LTD.  
6. Sample Conformity as per Decision Rule No.-1.  
7. Test Result relates to the Tested Item only.



Authorised Sign  
(Dr. Amit Bishnoi)  
(Technical Head)

## **WIDMANS LABORATORY (P) LTD.**

PLOT NO. 155 E, SECTOR – 7, IMT MANESAR GURGAON, HARYANA (INDIA) 122050

Tel: (0124)4014550, +91-9810930809, +91-9999370036 Mail: [mail@widmanslab.com](mailto:mail@widmanslab.com) Web: [www.widmanslab.com](http://www.widmanslab.com)





# TEST REPORT

<b>Report Issued To</b>	<b>Diamond International Inex Pvt Ltd</b>	<b>Report No.</b>	<b>N5104</b>
	Plot 98, Sec 8, IMT Manesar, Gurgaon, Haryana 122050	<b>ULR-</b>	<b>TC733224000004215F</b>
		<b>Date Received</b>	<b>12-02-2024</b>
		<b>Date Issued</b>	<b>15-02-2024</b>

**Coating Thickness Test (DFT)**

**Test Method : IS 101 (PART 3) SEC-2:1989-RA 2019**

**Date of Testing :13-02-2024**

Temp - 23±5°C

S.No	Observation	Unit
1.	137	Micron
2.	140	Micron
3.	142	Micron
4.	138	Micron
5.	139	Micron
6.	142	Micron
<b>Average</b>	<b>139.67</b>	<b>Micron</b>

Testing Engineer: Indra Pratap

-----End of Report-----



Authorised Sign  
(Dr. Amit Bishnoi)  
(Technical Head)

**WIDMANS LABORATORY (P) LTD.**

PLOT NO. 155 E, SECTOR – 7, IMT MANESAR GURGAON, HARYANA (INDIA) 122050

Tel:(0124)4014550,+91-9810930809,+91-9999370036 Mail: [mail@widmanslab.com](mailto:mail@widmanslab.com) Web: [www.widmanslab.com](http://www.widmanslab.com)

